



Technical Data Sheet

Stainban™ 208 – Calcium Strontium Zinc Phosphosilicate

Stainban™ 208 is a white, non-refractive pigment especially designed to inhibit the migration of the tannin stains in coatings on a wide variety of woods. The small particle size and narrow particle distribution allows the pigment to be easily incorporated into the coating using high speed dispersion. It is compatible with a wide variety of solvent and water based resins. It is recommended for use in primers or in self-priming applications where stain inhibition is needed. Typical use levels range from 5 – 9% total formula weight.

Characteristic	Test Method	Typical Value
Appearance		White powder
Zinc as ZnO [%]		41 - 43
Phosphate as P ₂ O ₅ [%]		14 - 16
Silicate as SiO ₂ [%]		17 - 19
Calcium as CaO [%]		16 - 18
Strontium as SrO [%]		3 - 5
Specific Gravity	ASTM D-153	2.90
Bulking Value [gal/lb] [l/kg]		0.041 0.345
pH	ASTM D-1208	7.5 – 9.5
Moisture at 110 °C [%]	ASTM D-280	7.0 Max
Oil Absorption [lbs/100 lbs] [kg/100kg]	ASTM D-281	22 - 30
Apparent Bulk Density, Tapped [g/100 cm ³]		50 - 85
Fineness of Grind [Hegman Value]	ASTM D-1210	6.0 Min.
Mean particle size [microns]	Malvern Mastersizer	6.0

Suggested Applications
Acrylic latexes
Vinyl acrylic latexes
Styrenated acrylic latexes
PVA homopolymers
Solvent alkyds
Alkyd emulsions
Styrene butadiene (SBR)
Alkyds
Acrylic emulsions

Performance in other coating systems has not been evaluated.

These are typical values and do not represent specifications.

The information made herein is based upon our research and the research of others, and is believed to be accurate. No guarantee of accuracy is made and the product discussed is sold without warrant, expressed or implied and upon the condition the purchaser shall make their own tests to determine the suitability of such product for their particular purposes.

